## CLAIMS

5

10

25

- 1. Fire-insulating wall covering, comprising a cured mixture of:
  - i) 5-20% by weight mineralized wood fibre;
  - ii) 20-60% by weight sand with an SiO<sub>2</sub> content of less than 5% by weight and a greywacke content of at least 30% by weight; and
  - iii) 20-50% by weight cement.
- 2. Wall covering as claimed in claim 1, containing 7-15% by weight, preferably 10-15% by weight mineralized wood fibre.
  - 3. Wall covering as claimed in claim 1 or 2, containing 35-50% by weight sand.
- 4. Wall covering as claimed in claims 1-3, wherein the sand has an  ${\rm SiO_2}$  content smaller than 2.5% by weight,
- 15 preferably smaller than 2% by weight.
  - 5. Wall covering as claimed in claims 1-4, wherein the sand contains at least 40% by weight and preferably at least 50% by weight greywacke.
- 6. Wall covering as claimed in claims 1-5, containing 20 25-40% by weight cement.
  - 7. Wall covering as claimed in claims 1-6, containing:
  - i) 10-15% by weight mineralized wood fibre;
  - ii) 35-50% by weight sand with an SiO<sub>2</sub> content smaller than 2% by weight and a greywacke content greater than 50% by weight; and
    - iii) 25-40% by weight cement.
  - 8. Wall covering as claimed in claims 1-7, wherein the cement is low-chromate.

WO 2004/089847 PCT/NL2004/000237

9

- 9. Wall covering as claimed in claims 1-8, containing 0.1-1% by weight, preferably 0.1-0.5% by weight impregnating agent and/or 30-500 gram per m<sup>2</sup>, preferably 100-250 gram per m<sup>2</sup> impregnating agent.
- 10. Method of preparing a fire-insulating wall covering as claimed in claim 1, wherein relative to the cured weight are mixed 5-20% by weight mineralized wood fibre, 30-60% by weight sand with an SiO<sub>2</sub> content smaller than 5% by weight and a greywacke content of at least 30% by weight, and 20-50% by weight cement, and 10-30% by weight water is then added, whereafter the mixture is cured to form the fire-insulating wall covering.